

## CL0106-P

Properties	Unit	Test Method	Result
Butadiene / Styrene	–	D1416	67 / 33
Density	–	D792	0.95
MFI	g/10min	D1238	30
Tensile Strength	kgw/cm2	D624	80
Elongation	%	D412	600
Hardness	Shore A	D2240	50
Color			Colorless