

CL0106-S

Properties	Unit	Test Method	Result
Butadiene / Styrene	–	D1416	60 / 40
Density	–	D792	0.96
MFI	g/10min	D1238	12
Tensile Strength	kgw/cm2	D412	49
Elongation	%	D412	600
Hardness	Shore A	D2240	45
Color			Colorless