

CL0106-U

Properties	Unit	Test Method	Result
Butadiene / Styrene	–	D1416	67 / 33
Density	–	D792	0.97
MFI	g/10min	D1238	20
Tensile Strength	kgw/cm2	D412	132
Elongation	%	D412	730
Hardness	Shore A	D2240	90
Color			

CL0106-V

Properties	Unit	Test Method	Result
Butadiene / Styrene	–	D1416	70 / 30
Density	–	D792	0.98
MFI	g/10min	D1238	13
Tensile Strength	kgw/cm2	D412	164
Elongation	%	D412	740
Hardness	Shore A	D2240	65
Color			